



ARENA CLOTH SPECIFICATIONS

Construction	Microdenier Warp Knit --Courses: 55/in. +/-3 --Wales: 35/in. +/-2
Yarn	100% Polyester VISA IFR (Inherently Flame Retardant)
Fabric Width:	130 inches (+/- 1")
Fabric Weight:	6.75 oz. per yard ² +/-0.25 oz. 24 oz. per linear yard +/- 0.25 oz.
Roll Size:	approx. 90 yards (max 110/min 30) (max 2 (merrow) seams/roll; min 30 yards between seams) Tube is 134" with 3" ID
Country of Origin:	USA
Harmonized Code:	5516.22.9000
Flame Retardancy:	NFPA 701, test method #1 California Title 19, test #1227
Martindale Abrasion testing	1600 cycles wet: moderate minimum 3200 cycles dry: moderate minimum
Air Permeability	250 cfm
Shrinkage	2.5% X 2.5% max (5 cycle wash @ 120° F)
Defects per 100 yards	5 maj., 25 pts. Total
California Prop 65	<u>does not</u> trigger consumer labeling requirements

RoseBrand.com